



ARDEX CE 828

Structural Micro Concrete

Shrinkage compensated

High flexural and compressive strength

Self-compacting

Installs from 20mm to 100mm neat, and up to 250mm when extended with aggregate

For civil engineering and general construction



ARDEX-QUICSEAL SINGAPORE PTE. LTD.
26 Tuas Ave 4 Singapore 639376
Telephone: +65 6861 7700
Fax: +65 6741 4666
Email: sales@ardex-quickseal.com
Website: www.ardex-quickseal.com

ARDEX CE 828

Structural Micro Concrete

DESCRIPTION

ARDEX CE 828 Flowable Structural Micro Concrete is a pourable repair mortar designed for reinstating concrete structures damaged through concrete spalling and other chemical or mechanical causes. ARDEX CE 828 exhibits good flow characteristics and is capable of being applied in thickness of 20mm to 100mm in one pour.

RECOMMENDED USES

- Reinstatement of concrete beams and columns
- Bridge Bearings
- Bedding machinery plates
- Concrete pile grouting repairs for marine applications
- Normal service commercial, institutional, and multi-unit residential applications

ADVANTAGES

- High Flexural and Compressive Strength
- Dimensional stable
- High bond to concrete
- Chloride free
- Low permeability
- Suitable for deep pours

SURFACE PREPARATION

The substrate must be clean, sound, and free from all grease, oil, dust, laitance, and other surface contaminants such as curing membranes. Damaged or contaminated concrete must be removed to obtain a good bond to the substrate. Cut the edges of the repair vertically to a minimum depth of 20mm until the area is squared or boxed in shape. Greater depth is required for heavy-duty trafficable applications. Exposed reinforcing steel should be cleaned to remove all residual rust and concrete residue. Concrete should be removed from around and behind all corroding rebar to avoid future contamination of the repaired area. The substrate must be prepared correctly to remove all the deteriorated and detached concrete until a strong substrate with a rough surface is obtained. Any areas previously repaired and which are not perfectly bonded must also be removed.

PRIMING

To reduce the porosity of the substrate, priming the prepared substrate with ARDEX P 507 is recommended. Alternatively, the prepared substrate can be pre-soaked

using water for at least 2 hours before applying ARDEX CE 828. Remove excess freestanding water on the surface prior to the application of ARDEX CE 828. The surface should be damp to touch without standing water.

FORMWORK PREPARATION

The area to be pumped must be enclosed with good quality rigid watertight formwork. The formwork must be able to rigidly confine the ARDEX CE 828 until it has set. It is recommended to use an appropriate form release agent. Formwork should be flushed out just prior to an application without any standing water present.

MIXING

Each 25kg bag of ARDEX CE 828 will require approximately 3.25 – 3.75L of water. Measure approximately 80% of the required water into a clean suitable sized pail and then add the entire contents of the bag while mixing with a heavy-duty electric drill on medium speed (approximately 680rpm). Add the remaining water and mix for about 2 – 3 minutes or until it is fully homogenized. The mixed material must be poured immediately for best results.

APPLICATION

ARDEX CE 828 is to be applied onto the pre-wetted or primed substrate. Make sure that the micro concrete is applied whilst the substrate is still damp, or the substrate primer is still slightly tacky. It should be applied in a continuous pour to avoid cold joints. It is recommended to smooth the material with a steel trowel after the last pour. For ease and efficiency of application, ARDEX CE 828 can be pumped using a suitable automatic concrete mixing pump. Follow the instructions as set by the pump manufacturer.

ARDEX CE 828 can be installed from a minimum depth of 20mm to 100mm. For application depths greater than 100mm, and up to 250mm, extend ARDEX CE 826 by adding aggregates dampened to an SSD condition. Mix the aggregate with water first, and then ARDEX CE 828 until is fully homogenized.

CURING

As with all cementitious products, ARDEX CE 828 must be cured properly to ensure maximum performance. Apply ARDEX P 507 as a curing compound after initial set on all exposed areas. If form work is used,

ARDEX CE 828

Structural Micro Concrete

the curing compound should be applied immediately after the form work is removed. Curing compounds should be applied onto the surface of the ARDEX CE 828 according to the Technical Data Sheet of the curing compound. If a curing compound is not used, wet hessians and/or plastic sheets should be placed on the surface for 3-7 days.

PAY ATTENTION TO THE FOLLOWING:

1. Do not over-water. This can lead to segregation, shrinkage and strength reduction.
2. For long narrow repairs or thickness exceeding 100mm, contact ARDEX-QUICSEAL Singapore for advice.
3. Do not install below 10°C surface and air temperature
4. Store bags and water reservoir for mixing in a shaded or conditioned space. Cool water and powder can greatly extend the working time in hot

conditions.

PACKAGING

ARDEX CE 828 is packed in polylined paper sacks – net weight 25kg

STORAGE AND SHELF LIFE

ARDEX CE 828 has a shelf life of 12 months when stored in the original, unopened packaging in a dry place at 23°C and 50% relative humidity.

CLEAN UP

All grouting equipment shall be thoroughly washed with clean water after grouting operations for that day are completed.

SAFETY PRECAUTIONS

ARDEX CE 828 should not come into contact with the skin and eyes or to be swallowed. Ensure adequate

TECHNICAL DATA

Mixing Ratio	3.25 – 3.75L of water per 25kg bag
Coverage Pouring Consistency Pumping Consistency	25kg of powder yields 12.1L of grout @ 13% water 13.0L of grout @ 15% water 1m ³ of grout requires 77bags of powder @ 15% water

Characteristics	Test Method	Test Results
Compressive Strength 1 day 7 days 28 days	BS EN 12190 : 1999	≥ 8 MPa ≥ 50 MPa ≥ 75 MPa
Flexural Strength 7 days 28 days	BS EN 196-1 : 2006	≥ 5 MPa ≥ 7 MPa
Change in Height	ASTM C1090 : 2015	0% to 1%
Chloride Content	BS EN 1015-17 : 2000	≤ 0.02%
Time to Traffic	Visual	Foot: > 12 hr Vehicular: > 24 hr
Fresh Density	BS EN 1015-17-2000	2250 ± 100kg/m ³
Setting Time	ASTM C953 : 2010	Initial Set > 2 hr Final Set < 12 hr

Technical data according to ARDEX Quality Standards. All data based on a partial, in-lab mix at 23±2°C and RH 55±10%, water powder ratio 0.14.

ARDEX CE 828

Structural Micro Concrete

ventilation and avoid inhalation of vapors. Wear suitable gloves, goggles and other protective clothing. The use of barrier creams can provide additional skin protection. When working in confined areas suitable respiratory equipment must be used. In case of contact with skin, rinse with plenty of clean water then wash with soap and water. Do not use solvent. In case of contact with eyes, rinse immediately with plenty of clean water, and then seek medical attention without delay. If swallowed, seek medical attention straight away, do not induce vomiting. The Safety Datasheet (SDS) is available at www.ardex-quicseal.com

DISPOSAL/SPILLAGE

Please refer to the Safety Data Sheet for the safe handling, storage and disposal of chemical products.

DISCLAIMER

The technical datasheets are based on the latest information and given in good faith and represent the best of our knowledge and experience at the time of printing. They are primarily offered for users' consideration and evaluation. It is the responsibility of the user to conduct their own tests to validate the suitability of the products. It is also the responsibility of the user to ensure that the products are used and handled correctly and in accordance with any applicable standards, the product instructions, and recommendations and only for the uses they are intended. As we have no control over site conditions and the execution of the work, we accept no liability for any loss or damage which may rise as a result thereof. We also reserve the right to update the information at any time without prior notice to you to reflect our ongoing research and development program.

Offices:

ARDEX QUICSEAL MALAYSIA SDN. BHD.
72-2, Jalan Puteri 2/2 Bandar Puteri 47100,
Puchong, Selangor Darul Ehsan
Malaysia
Phone: +603 8051 0311
Email: sales.malaysia@ardex-quicseal.com

Thailand:
ARDEX (THAILAND) CO., LTD
969 2nd Floor Moo, 13, Soi 45, Bangna-Trad Road
Bangkaew, Bangplee, Samutprakarn 10540
Thailand
Tel: +66 2316 3069 Fax: +66 2316 3075
Email: sales@ardex.co.th

Vietnam:
Mobile: +84 901 351 308
Email: sales@ardex-quicseal.com

Hong Kong:
ARDEX SCORETECH LIMITED
1101 New Mandarin Plaza Tower B
14 Science Museum Road, TSTE
Telephone: +852 2529 6325 / +852 2165 0900
Email: sales@ardexscoretech.com

JAN 2025 T