

Estoflex Acryl 1000

Decorative, Elastomeric Waterproof Membrane for Roof

Description

Estoflex Acryl 1000 is a single component, solvent free, water dispersed vinyl-ethylene copolymer, thus providing prolonged durability and excellent weather resistant and its latex properties completely resist ozonolysis and other oxidative degradation.

Colours incorporated are oxide pigments, thereby resistant to ultra violet light with no deterioration especially in tropical conditions.

Estoflex Acryl 1000 is also very useful for complete waterproofing with decorative finish on corroded corrugated metalsheets and concrete roof slab.

Estoflex Acryl 1000 has been tested by SIRIM BHD, in accordance to BS 1881 Part 122:1983, on Water Absorption Test; ASTM D412 : 2002, on Ultimate Tensile Strength and Elongation and complied with the specification in this data sheet.

Uses

Estoflex Acryl 1000 is a brush or roller applied decorative treatment for:-

- Old or new roofs
- Concrete, asbestos cement, corrugated roof, felt timber etc. but excluding bitumen

Advantages

- Durable/Flexible
- Provide a complete roof protection
- Excellent opacity/Low odour
- Single component/Water base
- Decorative waterproofing coating
- Simple to apply by brush or roller/Economical
- Excellent adhesion to metal and concrete
- Capable of bridging substrate crack up to 1.5mm when fully cured at 1.2mm thick

Standards Compliance

- **BS 1881, Part 122 : 1983**
- **ASTM D412 : 2002**

Physical Properties

Water Absorption,% BS 1881 Part 122 : 1983	<0.1
Ultimate Tensile Strength, MPa ASTM D412 : 2002	>2.0
Ultimate Elongation, % ASTM D412: 2002	>200

Application Instructions

Surface Preparation

All surfaces should be generally sound and clean. Cracks and joints should be cleaned and filled with **Estoflex Acryl 1000** separately, allowing drying. Larger cracks should be chased out to at least 10 mm wide and repaired with Estop joint sealing compounds such as Estojoint or Estolastic.

Base Screed (for R. C. flat roof)

Base screed with minimum gradient of 1:120, to receive **Estoflex Acryl 1000**, shall be laid if the floor is uneven and without required gradient, to achieve better waterproofing performance.

Application

General specification clauses for Estoflex Acryl 1000 on RC roofs.

The surface shall be cleaned and free from dust, dirt, grease, moss and loose material. The clean surface shall be primed by brushing the surface with 5 part **Estoflex Acryl 1000** mix with 1 part of clean water and at a spread rate of 5 - 6 m²/litre. Allow primer coat to cure. The priming coat shall be extended at least 240mm up to all parapet walls.

The primed surface shall be over coated with the first undiluted coat of **Estoflex Acryl 1000** at spread of 3 – 4 m²/litre. Whilst firstcoat is still sticky, embed Estop fibreglass on top of it and allow drying.

After the first coat application, sprinkle Estop Slip Resistant Grain at 2kg/m², before applying of second coat of **Estoflex Acryl 1000** at spread rate of 3 – 4 m²/litre.

This is to enhance durability and to provide slip resistant surface.

An additional of third coat of **Estoflex Acryl 1000** at the spread of 2m²/liter is optional, depending on requirement.

Once **Estoflex Acryl 1000** has hardened, it is then immune to weathering and dampness. **Estoflex Acryl 1000** may be diluted with water if thickens on standing.

Estoflex Acryl 1000 is very effective when sandwiched with Estop fibreglass to repair leaky gutters, down spouts, etc. to bridge cracks; corrosion etc. providing the damage is not too extensive. Do not pour surplus materials down drain, wash all brushes immediately or keep immersed in water.

a) Non-Expose System – Protective Screed

If sand and cement protective panels are required for roof traffic on top of **Estoflex Acryl 1000**, the above final coat of **Estoflex Acryl 1000** should be blinded with clean sharp sand passing through a 3 mm sieve to provide a key for the second concrete pour.

b) Exposed System

Estoflex Acryl 1000 is also an expose decorative waterproofing system. It comes in various colours as stated in this data sheet.

Packing & Size

Estoflex Acryl 1000	20 litre pail
Colours	Off White, Grey, Green (Special colours on request)

Coverage

Estoflex Acryl 1000	3 – 4 m ² /litre/coat, depends on porosity of surface
----------------------------	--

Technical Support

Denka offers a comprehensive technical support, including help at the design stage, application advice and on the site problem solving. Specifiers and contractors are encouraged to contact our trained staff for answers to their questions.

Storage

Storage must be carefully controlled as all latex systems may coagulate (solidify with long periods of storage) in high temperatures. Store in shade under warehouse conditions and keep away from sources of heat.

Estoflex Acryl 1000 has a minimum shelf life of 12 months.

Shelf life may reduce if stored in extreme heat condition.

Precaution

Estoflex Acryl 1000 should not be swallowed or in contact with skin and eyes. Wear suitable protective gloves and goggles.

Splashes on the skin should be removed with water. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting.

Additional Information

Denka Construction Solutions Malaysia Sdn Bhd also offers various types of waterproofing systems, which include self-

adhesive, and torched-on membranes, polymer modified cementitious coatings, liquid applied coatings and rubberized bituminous emulsions etc.



Denka Construction Solutions Malaysia Sdn Bhd
(591858-U)

No. 18, Jalan Utas 15/7, Seksyen 15,
40200 Shah Alam, Selangor Darul Ehsan, Malaysia
Tel: +603 5510 8810 Fax: +603 5518 8202
www.denka-cs.com

Limitation of Liability

The information contained in this brochure provides general advice for potential customers for DENKA about the basic properties and characteristics of various DENKA products (hereafter known as "the Product Information"). DENKA makes no warranty or representation as to the entire accuracy or completeness of the Product Information in the brochure. Nothing in this brochure will be deemed to create any express or implied warranty of merchantability, fitness for a particular purpose or infringement of any intellectual property rights. Each user of the Product Information and DENKA products assumes their own responsibility to properly determine the manner and suitability of use of the Product Information and DENKA products in its own operations. The user should exercise proper care in considering the Material Safety Data Sheet, Product Information and any other technical information provided by DENKA including descriptions of the conditions of use, warnings and other cautionary instructions. DENKA reserves the right to change the Product Information from time to time at its discretion and without notice.