

Estoflex Solar 690

PURE Polyurea Waterproofing Membrane

Description

Estoflex Solar 690 is a rapid curing, chemical resistant **PURE** Polyurea, spray applied waterproofing membrane. **Estoflex Solar 690** consists of 2 components, ISO and Amine. In view of environmental concerns, it is solvent free and MDI as an isocyanate with low vapour pressure is added. 100% solids pre-heated, flexible, two-component polyurea elastomeric waterproofing membrane with excellent resistance to wide range of aggressive chemicals condition. The seamless coating provides an elastic yet tear resistant surface for applications subjected to extreme wear and tear, strong impact and chemical exposure. As with all aromatics, over a period of time colour change will occur if exposed to UV rays. This will not have any negative effect on the physical properties of the product. Suitable for outdoor applications. Available in wide range of attractive colour.

If long term aesthetics and excellent UV resistance is required, then spray/roller apply Estoflex Solar TC60 as topcoat is recommended.

Uses

Estoflex Solar 690 is suitable for indoor and outdoor applications as below:

- Waterproofing for commercial, industrial & manufacturing facilities.
- Sealing and substrate protection – Plant rooms, trafficable roof decks.
- Waterproofing and substrate protection for area exposed to high wind abrasion.
- Under concrete screed waterproofing of large-scale podium decks where residual moisture exists.
- Bridge, street and tunnel waterproofing particularly in high moisture environments.
- Lining of non-portable water tanks, wastewater tanks.
- Loading docks and access ramps.
- For all waterproofing containment applications where there are no aggressive chemical and abrasive forces.

Advantages

- Can be applied even under extreme climate condition. Hot, cold and humid conditions.
- Good elongation and tensile strength.
- Environmental friendly – zero VOC
- Seamless and rapid curing.
- Hard wearing – exhibits excellent impact, abrasion and puncture resistance.
- Elastic – bridge cracks on concrete surface.
- Excellent adhesion to concrete, steel, aluminum, plastic, fibers, wood, foam, etc.
- Rapid application to any thickness and very fast cure results in faster turn around times.
- 100% solid, VOC -free and contain zero solvents.

Standard Compliance

- **ASTM D412:2016**
- **ASTM D2240**
- **ASTM D4541**
- **ASTM E154/E154M-2008a**

Physical Properties

Solid Content	100%
Colour	Straw/Brownish colour Un-pigmented
Mixing Ratio	1 to 1 by volume
Recommended Thickness, mm	Minimum: 1mm on steel Max: Unlimited 1.5mm to 2.5mm on concrete
Gel Time at 20°C, sec	5 – 10 (depend on ambient and substrate temperature)
Tack Free Time at 20°C, sec	15 – 30 (depend on ambient and substrate temperature)
Curing / Loading, hour	
Walkable	1
Mechanical	2
Chemical	12 - 24
Tensile Strength, N/mm ² ASTM D412:2016	≥17
Elongation, % ASTM D412:2016	≥300
Shore D Hardness ASTM D2240	45 ± 5
Tear Growth Resistance, N/mm ISO 34-1	≥15
Viscosity at 25°C, mPa*s	
Component A	300 – 1000
Component B	600 – 1350
Density, g/cm ³	
Component A	1.09 – 1.13
Component B	0.98 – 1.02
Mix	1.00 – 1.04
Adhesion to substrate, N/mm ² (ASTM D4541)	
Concrete	≥ 1.5
Steel	≥ 5.0
Puncture Resistance, N ASTM E154/E154M-2008a	≥1000

Application Instruction

Surface Preparation

The surface must be sound, free of any laitance, loose and crumbly particles, and must be clean and free of products that can impair or inhibit adhesion of the primer or coating. (e.g. oil, grease, paraffin, rubber debris, release agents, post-treatment agents, organic additions, paint residues). The surface must neither be floury nor sandy.

240903

Priming

It is recommended to apply **Estoprime LV** at rate of 5m²/L on the well-prepared concrete substrate and allow to dry before the spraying process.

Application

This material is designed for application with heated, plural component airless spray equipment.

Actual spray trial shall be conducted to confirm the spray equipment adjustment.

Notes:

The gel time and tack free times depend on the surrounding climatic conditions, temperature, relative humidity and ventilation. Therefore, above specified data can only be used as a guide.

Packaging

Estoflex Solar 690 Part A	225 kg drum
Estoflex Solar 690 Part B	200 kg drum
Estoprime LV	5L/ set

Cleaning

Estoflex Solar 690 should be removed from tools and equipment immediately after use with suitable solvent.

Coverage

Estoflex Solar 690	1.0kg/m ² @ 1.0mm thickness
Estoprime LV	5m ² /L

The coverage will depend on porosity of substrate surface to receive **Estoflex Solar 690**.

Technical Support

Denka manufactures and offers a technical support package to specifiers, end-user and contractors, as well as on site technical assistance.

Storage

Estoflex Solar 690 has a shelf life of 12 months in unopened containers, kept in a dry store. In high humidity locations, the shelf life may be reduced. It is recommended to store at 10-30°C (in closed original drums stored at dry and well-ventilated place, do not allow to freeze)

Precautions

Gloves and goggles should be worn. Any splashes to the skin or eyes should be washed off with plenty of clean water. In the event of prolonged irritation, seek medical advice. Application areas must be well ventilated.

Additional Information

Denka Construction Solutions Malaysia Sdn Bhd offer a wide range of complementary products which includes waterstops, waterproofing products, grouts, anchors, specialized flooring products. In addition, a wide range of products formulated for repair and refurbishment of spalled concrete are available.



Denka Construction Solutions Malaysia Sdn Bhd
(591858-U)

No. 18, Jalan Utas 15/7, Seksyen 15,
40200 Shah Alam, Selangor Darul Ehsan, Malaysia
Tel: +603 5510 8810 Fax: +603 5518 8202

www.denka-cs.com

Limitation of Liability

The information contained in this brochure provides general advice for potential customers for DENKA about the basic properties and characteristics of various DENKA products (hereafter known as "the Product Information"). DENKA makes no warranty or representation as to the entire accuracy or completeness of the Product Information in the brochure. Nothing in this brochure will be deemed to create any express or implied warranty of merchantability, fitness for a particular purpose or infringement of any intellectual property rights. Each user of the Product Information and DENKA products assumes their own responsibility to properly determine the manner and suitability of use of the Product Information and DENKA products in its own operations. The user should exercise proper care in considering the Material Safety Data Sheet, Product Information and any other technical information provided by DENKA including descriptions of the conditions of use, warnings and other cautionary instructions. DENKA reserves the right to change the Product Information from time to time at its discretion and without notice.