

Estoproof 30

High Performance Multi-Purpose Damp Proof Membrane

Description

Estoproof 30 is a high-performance damp-proof membrane made from a prime virgin base material to 300 ± 20 microns (0.30 ± 0.02 mm) thick perfect for providing damp proofing security throughout the lifetime of a building.

Estoproof 30 has been tested, in accordance to ASTM D882:2018, on the Elongation at Break and Tensile Strength Test, and complied with the specification in this data sheet.

Uses

Estoproof 30 is the premium quality permanent and efficient damp proof membrane for use: -

- Under reinforced concrete ground, basement slabs and underground structures.
- On top of the slab and below 50 mm thick (minimum) cement and sand floor screed.
- On top of insulation foam board as separation and protection layer.
- On top of lean concrete as separation layer and vapour barrier in the application of spray waterproofing membrane system.
- On top compacted earth as supplemental vapour barrier in basements and underground structures waterproofed with hydrophobic waterproofing admixture system.
- On top soil as protection layer against erosion.

Advantages

- High tensile strength.
- High elongation and flexibility.
- Easy to apply and rapid application rate.
- Highly reflective, can be exposed to sunlight.
- Simple on-site overlap sealing with adhesive tape.
- Biological resistance- unaffected by bacteria, fungi, etc.
- Chemical resistance to all naturally occurring subsoil alkalis and acids.

Standards Compliance

- **ASTM D882:2018**
- **ASTM E154/E154M-08a(2013)e1**

Physical Properties

Tensile Strength, MPa ASTM D882:2018	> 20
Elongation at Break, % ASTM D882:2018	> 1000
Puncture Resistance, N	>150
Dimensional Stability	+/- 5%

Application Instructions

Installation

Estoproof 30 is used as an over-site membrane situated between the base concrete and the hardcore bed. A blinding layer of sand or granite quarry dust on a well compacted hardcore provides a suitable base. The membrane suited in this position protects the site concrete against any sulphate attack and allows good bonding of screed to the concrete.

Jointing the Laps

It will at times be necessary to joint membranes together and to tailor the membrane round projections etc. prior to any jointing being made, sheets must be clean and free from dirt and grease. Adjacent sheets are overlapped by at least 100 mm. The lapping shall be sealed with wide premium quality adhesive tape or its equivalent to complete the overlap sealing process. The above techniques have been found suitable and effective for installation even by unskilled workers.

Packing & Size

Estoproof 30	90m ² per roll
---------------------	---------------------------

Technical Support

Denka offers a comprehensive range of high performance, high quality of product for both new and existing concrete surfaces, in addition, the company offers a technical support package to specifiers, end-user and contractors, as well as on-site technical assistance.

Storage

Estoproof 30 should be stored in protected, dry areas. When left in an unopened package, **Estoproof 30** will maintain their design performance characteristic for 2 years.

240510

Additional Information

Denka Construction Solutions Malaysia Sdn Bhd offers a wide range of complementary products, which includes waterstops, waterproofing products, grouts, anchors, specialized flooring products. In addition, a wide range of products formulated for repair and refurbishment of spalled concrete are available.



Denka Construction Solutions Malaysia Sdn Bhd
(591858-U)

No. 18, Jalan Utas 15/7, Seksyen 15,
40200 Shah Alam, Selangor Darul Ehsan, Malaysia
Tel: +603 5510 8810 Fax: +603 5518 8202
www.denka-cs.com

Limitation of Liability

The information contained in this brochure provides general advice for potential customers for DENKA about the basic properties and characteristics of various DENKA products (hereafter known as "the Product Information"). DENKA makes no warranty or representation as to the entire accuracy or completeness of the Product Information in the brochure. Nothing in this brochure will be deemed to create any express or implied warranty of merchantability, fitness for a particular purpose or infringement of any intellectual property rights. Each user of the Product Information and DENKA products assumes their own responsibility to properly determine the manner and suitability of use of the Product Information and DENKA products in its own operations. The user should exercise proper care in considering the Material Safety Data Sheet, Product Information and any other technical information provided by DENKA including descriptions of the conditions of use, warnings and other cautionary instructions. DENKA reserves the right to change the Product Information from time to time at its discretion and without notice.