

## Estoproof 3P

### APP High Performance Plastomeric Torch-Applied Waterproofing Sheet Membrane

#### Description

**Estoproof 3P** is a high-performance APP Modified bituminous Torch applied waterproofing membrane; it is reinforced with non-woven spun bonded fibre rot proof polyester.

The underside of **Estoproof 3P** is finished with a light polyethylene foil. This increases flame-torching efficiency, reduces gas consumption and also protects the rolls during transport, handling and storage.

**Estoproof 3P** are composed of bitumen that is modified by APP, an atactic polypropylene polymer. The mixing has ensured that a true matrix inversion taken place, where the APP forms a continuous skeleton network with the bitumen filling up the void. This result in much better cold flexes temperatures and aging resistance.

**Estoproof 3P has been tested in accordance to BS EN 544: 2011, on Water Absorption Test and complied with the specification in this data sheet.**

#### Uses

**Estoproof 3P** is used for the waterproofing at new construction and in renewal work. It is suitable and widely been used at: -

- Concrete Roofs and floor slab
- Retaining walls
- Plaza decks
- Balconies / Terraces
- Basement tanking
- Tunnels and subways

#### Advantages

- Reinforced, high strength, minimizing risk at site damage
- Easy to install and bond well to substrate
- Remain excellent, flexibility even at low temperatures
- Dimensionally stable
- Excellent and durable for Tropical climates and light foot traffic.
- Resistant to hydrostatic pressure (up to 15m head of water)

#### Standards Compliance

- BS EN 12310-1
- BS EN 12311-1
- BS EN 544: 2011
- EN 1297

#### Physical Properties

Membrane Thickness, mm <b>Estoproof 3P (Sanded)</b>	3
Areic Mass, kg/m <sup>2</sup> <b>Estoproof 3P (Slated)</b>	4.0
Tear Resistance, N (BS EN 12310-1) Longitudinal Transversal	140 ± 42 160 ± 48
Elongation, % (BS EN 12311-1) Longitudinal Transversal	30 ± 15 30 ± 15
Tensile Strength, N/5cm (BS EN 12311-1) Longitudinal Transversal	600 ± 150 400 ± 150
Water Absorption, % BS EN 544: 2011	< 0.25
Water Vapor Permeability, μ x 1.000 EN 1931	20 (Default)
Resistance to Static Loading, kg EN 12730-A	15
UV Ageing (Visible Defects), EN 1297	Pass
<b>* These values are typical results obtained under laboratory conditions and are not intended as minimum specifications.</b>	

#### Application Instructions

##### Surface Preparation

For R.C Flat Roof application, the flat roof shall have a gradient of 1:120 minimums.

Base screed (cement sand mix of about 1:4) is normally recommended.

Substrates should be cleaned and free from loose aggregate, form release agents and other contaminants.

All critical right-angle bends must have a mortar angle fillet installed prior to application of **Estoproof 3P**.

##### Application Methods

**Estoproof 3P** can be loosely laid or fully bonded.

##### (A) Non-Expose System

For loosely laid application, the rolls are unrolled over the roof surface. Torching must carefully seal the overlaps. The membrane is then adequately ballasted against wind uplift.

For fully bonded application, all substrates must be primed with **Estoproof Primer W** at a rate of 4 - 6 m<sup>2</sup>/kg and allowed to dry.

Torch applies one layer of **Estoproof 3P** maintaining side laps of 50mm-75mm and end laps of 100mm-150mm. Fully heat weld sheet to the primed substrate.

Ensure that all laps are fully heat welded and finished with a heated spatula or propane gas torch, thus cause surface melting and subsequent adhesion to the surface.

250702

## Protection

### For Horizontal Application

Estoproof membrane shall be protected with protective screed and or other approved protection system before other trades of works.

### For Vertical Application

An approved protection board should be installed over the membrane prior to backfilling or covering the system with gravel.

### (B) Expose System

**Estoproof 3P Slated** (mineral finished) are recommended to be used as an exposed waterproofing system where the protective screed is not required.

## Packing & Size

<b>Estoproof 3P</b>	1m x 10m roll
<b>Estoproof Primer W</b>	200 kg drum 18 kg pail

**Estoproof 3P** come in two types of finishing

- **Sand Finished** (Non-expose system)
- **Slated Finished** (Expose system)

Note: Aluminium faced range and double reinforced torch membranes are available upon request.

## Technical Support

**Denka** offers a comprehensive range of high performance, high quality of product for both new and existing concrete surfaces. In addition, the company offers a technical support package to specifiers, end-users and contractors, as well as on-site technical assistance.

## Storage

**Estoproof 3P** membrane should be stored in original unopened packaging in dry conditions.

**Estoproof 3P** have a shelf life of 24 months.

However, membrane shall be stored vertically and not stacked.

## Precaution

Protection gloves are necessary when using the gas torch to install **Estoproof 3P** membrane.

## Additional Information

**Denka Construction Solutions Malaysia Sdn Bhd** offers a wide range of complementary products which includes waterstops, waterproofing products, grouts, anchors, specialized flooring products. In addition, a wide range of products formulated for repair and refurbishment of spalled concrete are available.



**Denka Construction Solutions Malaysia Sdn Bhd**  
(591858-U)

No. 18, Jalan Utas 15/7, Seksyen 15,  
40200 Shah Alam, Selangor Darul Ehsan, Malaysia  
Tel: +603 5510 8810 Fax: +603 5518 8202

[www.denka-cs.com](http://www.denka-cs.com)

## Limitation of Liability

The information contained in this brochure provides general advice for potential customers for DENKA about the basic properties and characteristics of various DENKA products (hereafter known as "the Product Information"). DENKA makes no warranty or representation as to the entire accuracy or completeness of the Product Information in the brochure. Nothing in this brochure will be deemed to create any express or implied warranty of merchantability, fitness for a particular purpose or infringement of any intellectual property rights. Each user of the Product Information and DENKA products assumes their own responsibility to properly determine the manner and suitability of use of the Product Information and DENKA products in its own operations. The user should exercise proper care in considering the Material Safety Data Sheet, Product Information and any other technical information provided by DENKA including descriptions of the conditions of use, warnings and other cautionary instructions. DENKA reserves the right to change the Product Information from time to time at its discretion and without notice.